North Carolina Department of Transportation
Division of Highways
Materials and Tests Unit
Raleigh, NC 27611

Materials and Tests Unit
*X-Cut Test Form**

Date		*Job #*	
Contract #		*County*	
Coating System		*Bridge #*	

PC MRK or AREA	*Wet Bulb*	*Dry Bulb*	*Steel Surface Temp*	*Dew Point*	*Humidity %*	*Adhesion Rating** (3A Minimum)*	*Failure Location*	*Pass Fail*

**Testing IAW ASTM D 3359, Test Method A*

** *5A- No peeling,*
4A-Trace peeling or removal along incision or at their intersection
3A- Jagged removal along incision up to 1.6mm (1/16") on either side
2A- Jagged removal along most of incisions up to 3.2 mm (1/8") on either side
1A- Removal from most of the area of the X under the tape
0A- Removal beyond the area of the X

Test Performed By	
Test Witnessed By QC/DOT	